

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09K 11/06, H05B 33/14, C07D 401/00	A1	(11) International Publication Number: WO 98/55561 (43) International Publication Date: 10 December 1998 (10.12.98)
(21) International Application Number: PCT/GB98/01587 (22) International Filing Date: 1 June 1998 (01.06.98) (30) Priority Data: 9711237.9 2 June 1997 (02.06.97) GB (71) Applicant (for all designated States except US): ISIS INNOVATION LIMITED [GB/GB]; 2 South Parks Road, Oxford OX1 3UB (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): CHRISTOU, Victor [GB/GB]; The University of Oxford, Inorganic Chemistry Laboratory, South Parks Road, Oxford OX1 3QR (GB). (74) Agent: STEVENS, Ian, Edward; Stevens, Hewlett & Perkins, 1 St. Augustine's Place, Bristol BS1 4UD (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GR, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: ORGANOMETALLIC COMPLEXES (57) Abstract Organometallic complexes comprising a trivalent lanthanide metal ion complexed with one or more polydentate ligands containing one or more pyrazolyl-derived groups, such as trispyrazolyl borate species, are useful in light emitting materials e.g., in electroluminescent flat panel displays. In the complexes, several classes of which are novel, a coordinate bond is formed between the metal and one of the nitrogen atoms of the pyrazolyl rings.		

10/773029



020504

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

ORGANOMETALLIC COMPLEXES

This invention relates to organometallic complexes, processes for their production, light emitting materials incorporating the complexes and light emitting devices comprising the complexes or the materials. The devices of the invention may be flat panel displays.

Flat panel displays are the critical enabling technology for many current applications, including laptop computers and "heads up" displays, as they offer several potential advantages over conventional cathode ray tube displays, including compactness and low power consumption.

Currently, the flat panel display market is dominated by liquid crystal technology, but these materials suffer several drawbacks including small operational viewing angles, poor image contrast and high power consumption. As an alternative technology for flat panel displays, electroluminescent displays using semiconducting organic polymers offer the potential of lower cost, improved viewing angles, better contrast and lower power consumption. However, these materials often have broad emission profiles, resulting in poor chromaticity and reduced device efficiency.

Typically, a flat panel device is a multilayer assembly of structurally important films consisting of a transparent electrode, insulation, phosphor and metal electrode. All are important materials in device fabrication, but the single most important element in the

development of a multi-colour electroluminescent device is the phosphor.

It is known that organometallic complexes can be used as phosphors in electroluminescent devices. For example, US 5552547 describes complexes of aluminium, gallium and indium in which one of the ligands acts as a "built-in" fluorescent dye. The colour of the light which is emitted from the complex is determined by the ligand which acts as the dye.

It has been suggested that lanthanide complexes can be used as phosphors in electroluminescent devices.

M. A. Pavier et al., Thin Solid Films, 284-285 (1996) 644-647, describe electroluminescence from dysprosium- and neodymium- containing Langmuir-Blodgett films. The ligand used in the complexes is a pyrazolone-based molecule in which the binding to the metal by the ligand occurs via a beta-diketonate-type arrangement.

The europium complex with phenanthroline and thenoyltrifluoroacetone is disclosed in Sano et al, Jpn. J. Appl. Phys., vol.34 (1995), p. 1883-1887 and Campos et al in J. Appl. Phys., vol.80, no.12 (1996), p. 7144-7150. Both Sano et al and Campos et al teach the use of the complexes to provide red light in electroluminescent devices. Like the complexes disclosed by Pavier et al, it is the beta-diketonate part of the ligand which binds to the metal.

Campos et al mentions that fluorination of part of the beta-diketonate ligand imparts higher sensitising efficiencies to the complex. The sensitising efficiency of a complex is a measure of the efficiency of the process of energy transfer from the ligand to the metal during the excitation step associated with electroluminescence.

Fluorination of beta-diketonate ligands in organolanthanide complexes has been proposed as a way of shielding the metal ion from quenching by water molecules when the complexes are in aqueous solution; see Meshkova et al, Sov. J. Coord. Chem., 18, 183 (1992). However, in most light emitting devices, metal complexes are either in the form of a thin film or are dispersed in a polymer matrix in the substantial absence of water molecules and so quenching of the metal ion does not occur by this mechanism. Therefore, the teaching of Meshkova et al, which is based on ensuring that water molecules cannot get close to the metal, is of little relevance to organometallic complexes for use in light emitting devices.

The present invention aims to provide organometallic complexes in which the metal is a lanthanide (i.e., organolanthanide complexes) which are more effective phosphors for use in light emitting devices than the known complexes.

The invention also seeks to provide a ligand system for organolanthanide complexes which is effective with a range of different lanthanides in order that the same ligand can provide radiation from different parts of the electromagnetic spectrum, e.g.,


red, green or blue light and UV or IR radiation, simply by varying the metal in the complex.

It is a further aim of the invention to improve the radiative efficiency of organolanthanide complexes. The radiative efficiency of an organometallic complex is a measure of the amount of energy which is radiated from the complex relative to the amount of energy lost via non-radiative pathways. The known organolanthanide complexes have the problem that a number of non-radiative pathways are available for energy loss from the metal and their radiative efficiencies can therefore be relatively low.

The present invention, in one embodiment, is based on the finding that pyrazolyl species are highly effective ligands for producing organolanthanide complexes useful as phosphors in light emitting devices. Accordingly, the invention provides a light emitting device comprising a complex containing a lanthanide metal cation complexed with from one to three polydentate ligands, wherein each ligand comprises one or more pyrazolyl groups, optionally substituted and optionally fused with a substituted or unsubstituted, heterocyclic or carbocyclic, aromatic or non-aromatic, ring system, one of the nitrogen atoms of the pyrazolyl groups forming a coordinate bond to the metal.

Preferably, the ligands are trispyrazolylborate anions, the pyrazolyl groups being optionally substituted and optionally fused with a substituted or unsubstituted, heterocyclic or carbocyclic, aromatic or non-aromatic, ring system, optionally substituted at the boron atom.

Suitable complexes for use in the invention are desirably those having the formula (I):



wherein Z is a carbon atom or R¹ - B fragment


p is 1, 2 or 3

q is 3-p

A is a counterion


R¹ is: (i) hydrogen, aryl or aralkyl each optionally substituted with from one to five halogen or C₁ to C₆ alkyl groups; or (ii) C₁ to C₆ alkyl, C₁ to C₆ alkenyl or C₁ to C₆ alkynyl each optionally substituted with one or more halogen atoms

each L is covalently bound to Z and is independently selected from a group of the formula (II) or (III)



(II)

or



(III)

in which R², R³ and R⁴ are independently selected from: (i) halogen, cyano, nitro, sulphonyl, amino, C₁

to C₆ alkylamino, C₁ to C₆ alkylamido, carboxyl, C₁ to C₆ alkyloxycarbonyl, hydroxy, C₁ to C₆ alkoxy, C₁ to C₆ alkylcarbonyloxy, C₁ to C₆ alkylcarbonyl C₁ to C₆ haloalkoxy and hydrogen; (ii) aryl or aralkyl each optionally substituted on the aryl ring or, for aralkyl, on the alkylene chain with from one or more of the groups mentioned under (i) above; and (iii) C₁ to C₆ alkyl, C₁ to C₆ alkenyl or C₁ to C₆ alkynyl each optionally substituted with one or more of the groups mentioned under (i) and (ii) above

or either R² and R³ or R³ and R⁴ are linked so as to form a fused, aromatic or non-aromatic, ring system with the pyrazolyl ring of L

and M is a trivalent lanthanide metal ion. p is suitably 1 or 2 and is preferably 2.

The light emitting device of the invention may be a flat panel display.

The complexes of formula (I) in which R⁴ and/or R² is -(CX₂)_nX wherein n is 0 or a positive integer from 1 to 6 and X is halogen; or R⁴ and/or R² is orthodihalogenated or orthodihalomethylated aryl, optionally further substituted on the aryl ring (e.g., with from one to three halogen atoms or C₁ to C₆ alkyl groups) or in which R² and R³ or R³ and R⁴ are linked so as to form a fused, aromatic or non-

aromatic, ring system with the pyrazolyl ring of L are believed to be novel and are also provided by the invention.

The term "alkyl" as used herein is intended to cover branched and unbranched C₁ to C₆ groups and alicyclic compounds for the C₃ to C₆ groups. The terms "alkenyl" and "alkynyl" are defined similarly with the only difference being that the groups may contain one or more unsaturated C=C bonds or C≡C bonds.

The term "aryl" covers C₆ to C₁₀ aromatic groups such as phenyl and naphthyl as well as heterocycles such as pyridyl, furyl and thiophenyl. The term "aralkyl" means C₁ to C₃ alkyl substituted with aryl, such as benzyl.

The term "halogen" means fluorine, chlorine, bromine or iodine. Of these, fluorine is the preferred halogen for the complexes of the invention.

Preferably, M is terbium (Tb), cerium (Ce), europium (Eu), erbium (Er), gadolinium (Gd), thulium (Tm), samarium (Sm) or neodymium (Nd). However, M may be another lanthanide metal such as praeodymium (Pr), for example. It will be appreciated that the metal is in the M (III) oxidation state in the complexes of the invention. The complexes with cerium, europium, erbium and gadolinium are preferred because they provide emissions of blue light, red light, IR radiation and UV radiation, respectively, and thus range across the electromagnetic spectrum. In electroluminescent devices, the complex with terbium unexpectedly gives blue light rather than the green light which is normally expected for terbium

complexes. This is particularly advantageous since cerium complexes which are conventionally used to produce blue light have the problem of a relatively wide bandwidth for the emitted light. The terbium complex of the present invention emits blue light with a narrower bandwidth than the previously used cerium compounds and so provides an improved alternative source of blue light for light emitting devices.

The trispyrazolyl ligands used in the invention have been found to be particularly effective in terms of their sensitising efficiency i.e., in transferring energy to the metal in the excitation step of the light emitting (e.g., electroluminescence) process. They also impart high radiative efficiencies to the complexes by providing few non-radiative pathways for relaxation (i.e., energy loss from the metal in its excited state). The ligands have been reported. Dias et al, Inorg Chem, 1995, 34, 1975 and 1996, 35, 267 and Renn et al Helv Chim Acta (1995), 78, 993 describe the synthesis of the fluorinated trispyrazolyl borate ligands. Julia et al., Organic Preparations and Procedures International, 16, 299, 1984, discloses the preparation of the trispyrazolylmethane-derived ligands.

The complexes of the invention are generally called "organometallic" herein. However, it will be understood by those skilled in the art that this term is used synonymously with the term "coordination". Also, the term "complex" as used herein covers both neutral species and compounds containing a charged organolanthanide species as part of a complex salt.


The present invention is also based on the wider finding that non-radiative pathways for relaxation in organolanthanide complexes can be provided by carbon-hydrogen bonds in the ligand which are relatively close to the metal and the discovery that these pathways can be blocked by fluorinating the ligand to replace the carbon-hydrogen bonds by carbon-fluorine bonds or otherwise designing the ligand such that there are no carbon-hydrogen bonds within 5 Å, preferably 8 Å, more preferably 10 Å, of the metal centre (i.e., the centre of the metal atom). Therefore, in another embodiment, the invention provides light emitting material comprising an organometallic complex either as a film or dispersed within a matrix of a polymer, the organometallic complex being a complex wherein the ligands are optionally fluorinated and arranged about the metal such that there are no carbon-hydrogen bonds within 5 Å of the metal centre.

The light emitted from the light emitting devices of the invention may be produced by various mechanisms such as electroluminescence, photoluminescence or cathodoluminescence with electroluminescence being preferred.

The matrix is preferably of the type conventionally used in light emitting (e.g., electroluminescent) devices and based on polymer systems such as polyvinylcarbazole (PVK) or polymethylmethacrylate (PMMA) with a hole transporting material such as 2-(4-biphenyl)-5-(5-tertbutylbenzene)-1,3,4-oxadiazole (BBO). The organolanthanide complexes used in the invention may themselves act as electron transporting materials, separately from or in addition to being a phosphor, in the light emitting devices.

The ligands ZL_3 used in the complexes of the present invention in which R^4 and/or R^2 is $-(CX_2)_nX$ or optionally substituted orthodihalogenated or orthodiperhalomethylated aryl are particularly advantageous for use in the electroluminescent material of the invention since they provide complexes with no carbon-hydrogen (C-H) bonds within 5 Å of the metal centre. However, it will be appreciated that other ligands can achieve the same effect and thus also block the non-radiative pathways for relaxation. It is notable that in all of the known complexes for use in matrices in light emitting devices mentioned above, carbon-hydrogen bonds are available for non-radiative relaxation.

In the complexes of the invention, R^4 and/or R^2 is conveniently trifluoromethyl. R^3 may be hydrogen and R^2 trifluoromethyl. Alternatively, ZL_3 may be:



Th increased conjugation of the fused bi- and poly- cyclic systems can be advantageous for electron transfer within the complex.


Where the complexes used in the invention are positively charged, they will be provided by compounds containing the complex and a counterion. The counterion preferably should not provide non-radiative pathways for relaxation of the metal. Therefore, it is preferred that the counterion should not contain bonds between hydrogen and other atoms, such as carbon-hydrogen bonds. Trifluoromethylsulphonate, CF_3SO_3^- , halide (fluoride, chloride, bromide or iodide), nitrate, NO_3^- , and perchlorate, ClO_4^- , are suitable counterions for this purpose.

In yet another embodiment, the present invention provides a process for producing the complex of the invention which comprises the steps of reacting M^{3+} ions (i.e., trivalent lanthanide ions) with ZL_3 anions in solution and separating the complex from the reaction mixture. The process is carried out in a suitable solvent at about or above room temperature up to the boiling point of the solvent for a time sufficient to form an extractable amount of the complex, preferably with stirring.

Preferably, the complex is separated from the reaction mixture by solvent extraction. To avoid the presence of water molecules in the complex which might provide non-radiative relaxation pathways, the process is preferably carried out under anhydrous conditions. It is also advantageous to exclude oxygen from the reaction mixture by

carrying out the process under an inert gas atmosphere e.g., of nitrogen or argon.

The process may be carried out via the following reaction:



wherein M' is a monovalent metal such as an alkali metal e.g., sodium or potassium, or thallium or silver (as Tl^+ and Ag^+ , respectively)

p, M, Z and L are as defined above,

and q is 3-p and A is a counterion.

In a preferred version of the process, two equivalents of $M'ZL_3$ are suspended or dissolved in a solvent and are treated with one equivalent of a trivalent lanthanide salt. The reaction mixture is stirred for a period of time between one and 100 hours either at room temperature or at the boiling point of the solvent under standard conditions. The solvent is removed (for example, by evaporation under reduced pressure) and the complex separated from by-products by extraction into a solvent with a different polarity from that of the reaction solvent. The product is purified by crystallisation from either the extraction solvent or a combination of solvents with different polarities.

The invention is illustrated, by way of non-limiting example only, by reference to the drawings in which:

Figure 1 shows a simplified cross-sectional view of an electroluminescent device according to the invention, such as an organic flat panel display;

Figure 2 is a current versus voltage plot for an electroluminescent device according to the invention;

Figures 3, 4 and 5 are photoluminescence plots for europium, terbium and cerium complexes of the invention; and

Figure 6 is a plot of electroluminescence intensity versus wavelength for an electroluminescent device of the invention containing a terbium complex of the invention.


The device 10 of Figure 1 includes a substrate 1 which generally has a substantially planar surface 1a and may be a glass plate, although other suitable materials can be used for this purpose. An electrically conductive layer 2 is deposited on the planar surface 1a so as to form a relatively uniform electrical contact. Layers 3, 4 and 5 may be a single layer (for example, of the electroluminescent material of the present invention) comprising a mixture of conductive materials and luminescent dopant (such as a complex of the invention). However, it is known that this results in reduced device efficiency and a more efficient working device consists of a first organic layer 3 of a hole transporting material, the host emissive material 4 (such as the electroluminescent material of the invention), a second organic layer 5 of electron transporting material (which may comprise an organolanthanide of the invention also useful as a

phosphor) and a second electrically conductive layer 6 to form a second electrical contact.

It will be appreciated that light generated within the host emissive material 4 can be emitted either through first organic layer 3, conductive layer 2 and substrate 1 or through second organic layer 5 and second conductive layer 6. In the device 10 depicted in Figure 1, substrate 1 is formed of glass and conductive layer 2 is formed of organic and inorganic conductors, such as conductive polyaniline (PANI) or indium-tin-oxide (ITO), which are substantially transparent to visible light so that the emitted light exits downwardly through substrate 1 as the device 10 is shown in the Figure.

Device 10 has a potential applied between layers 2 and 6 by means of a potential source 7. In the embodiment of the invention shown in the Figure, conductive layer 2 is a p-type contact and conductive layer 6 is an n-type contact. The negative terminal of potential source 7 is connected to conductive layer 6 and the positive terminal is connected to conductive layer 2. Electrons injected through the n-type contact are transported through organic layer 5 and into organometallic layer 4 (the emissive layer). Holes injected from the p-type contact are transported through the organic layer 3 and into the organometallic layer 4 where, upon an electron and hole recombination, a photon is emitted.

The invention will now be further described by the following examples which are not intended to limit the scope of the invention in any way. In the examples, $Tf = CF_3SO_3^-$ and

**EXAMPLE 1****[Ce(Bpz)₂(OTf)]**

A mixture of Ce(OTf)₃ (1.0g, 1.65 mmol) and KBpz (1.1g, 3.31 mmol) in THF (100 mL) were stirred at room temperature, under N₂. The solution gradually became yellow over 1 h. The mixture was left to stir for a further 14 h and the THF was then removed under reduced pressure to give a yellow residue. The product was extracted from the yellow residue with CH₂Cl₂ (50 mL). Subsequent removal of the CH₂Cl₂ *in vacuo* afforded the product as a pale yellow solid (0.69g, 47%). A photoluminescence plot for this complex is shown in Figure 5.

EXAMPLE 2**[Tb(Bpz)₂(OTf)]**

A mixture of Tb(OTf)₃ (1g, 1.65 mmol) and KBpz (1.1g, 3.31 mmol) in THF (100 mL) was allowed to stir for 14 h. During this time a colourless precipitate formed. The THF was removed under reduced pressure, the colourless residue treated with CH₂Cl₂ (2 x 50 mL) and the supernatant filtered. Removal of the CH₂Cl₂ under reduced pressure gave the product as a colourless microcrystalline solid (0.87g, 58%). A photoluminescence plot for this complex is shown in Figure 4.


An electroluminescent device was prepared using this complex as a phosphor. The device had a single layer structure consisting of a homogeneous mixture of the organometallic phosphor, an electron carrying material and a hole carrying material. This layer was deposited by spin-coating a stock solution of these materials onto an indium-tin oxide coated glass substrate in a dry nitrogen atmosphere. The stock solution was prepared in a dry nitrogen atmosphere using a mixture of the organometallic phosphor, polyvinylcarbazole (PVK) and 2-(4-biphenyl)-5-(5-tertbutylbenzene)-1,3,4-oxadiazole (BBO). This solid mixture was then dissolved in THF to give a solution having the following concentrations: [Tb(Bpz)₂(OTf)], 4.0 gdm⁻³; PVK, 20.0 gdm⁻³; BBO, 20.0 gdm⁻³. The counter electrode consisted of a magnesium contact overcoated with aluminium. A current versus voltage plot for the device is shown in Figure 2 and an electroluminescence intensity versus wavelength plot is shown in Figure 6.

EXAMPLE 3**[Eu(Bpz)₂(OTf)]**

A mixture of Eu(OTf)₃ (1g, 1.67 mmol) and KBpz (1.11g, 3.30 mmol) was suspended in THF (100 mL) and the mixture stirred at room temperature for 12 h. A fine pale precipitate formed after 1 h and the solution became pale yellow in colour. The THF was removed *in vacuo* and the product was extracted from the resulting pale yellow solid with CH₂Cl₂ (2 x 50 mL). Evaporation of the CH₂Cl₂ under reduced pressure gave the product as a pale yellow powder (1.16g, 78%). A photoluminescence plot for this complex is shown in Figure 3.

EXAMPLE 4**[Er(Bpz)₂(OTf)]**

Er(OTf)₃ (2g, 3.25 mmol) and KBpz (2.19g, 6.51 mmol) were mixed together under N₂ and THF (100 mL) was added. A fine colourless precipitate formed during the first 1 h of the reaction, whilst the solution remained a pale pink colour. This mixture was left to stir for 12 h overnight and then the THF was removed under reduced pressure. The pale pink product was extracted from the residue with CH₂Cl₂ (2 x 50 mL) and isolated as a powder by evaporation of the solution under reduced pressure (2.46g, 83%).

EXAMPLE 5

EuCl_3 (1g, 3.87 mmol) and KBpz (2.6g, 7.82 mmol) were mixed together under N_2 and THF (100 mL) was added. The resulting mixture was stirred for 1 h, by which time the solution had changed colour to orange and a fine colourless precipitate had formed. This mixture was left to stir for 14 h and then the THF was removed *in vacuo*. The product was extracted from the resulting pale yellow solid with CH_2Cl_2 (2 x 50 mL) and the resulting solution was then evaporated to dryness giving a pale yellow powder. This powder was washed with hexane (50 mL) and recrystallised from hot toluene to give the product as a yellow solid (0.48g). A second crop of crystals (0.87g) was obtained by concentrating the toluene supernatant (1.35g, 45%).

EXAMPLE 6

KBpf

A mixture of pf[H] (2.57 g, 12.6 mmol) and KBH_4 (0.12 g, 2.2 mmol) were suspended in dry decalin (20 mL) and the mixture was heated to 250 °C. After 4 h the mixture was cooled to room temperature and the pale yellow decalin solution filtered from the colourless sticky residue. The residue was triturated with pentane (50 mL), the pentane removed by filtration and the residue dried under reduced pressure to give the product as a colourless powder (0.62 g, 42 %).

Eu(OTf)₃ (0.257 g, 0.43 mmol) and KBpf(DMAC) (0.64 g, 0.86 mmol) were mixed under nitrogen and THF (100 mL) was added dropwise to the mixture at room temperature. After 26 hours, the THF was removed by vacuum and the product extracted from the resulting orange oil with THF (100 mL). The product was recovered from the THF solution as a pale brown solid by precipitation after concentration of the solution to 10 mL followed by addition of a large volume of hexanes (500 mL). The solid was dried under dynamic vacuum at room temperature for 4 hours.
Yield: 0.36 g (54%)

EXAMPLE 7

Tm(Bpz)₂(OTf)

A mixture of Tm(OTf)₃ (0.62 g, 1.0 mmol) and KBpz (0.67 g, 2.0 mmol) were dissolved in THF (50 mL) and the solution was stirred for 12 h at room temperature. A fine colourless precipitate developed within 1 h. After 12 h the THF was removed under vacuum and the product extracted from the resulting colourless solid with CH₂Cl₂ (50 mL). Removal of the CH₂Cl₂ *in vacuo* afforded the product as a colourless solid (0.72 g, 79 %).

EXAMPLE 8

Sm(Bpz)₂(OTf)

A mixture of Sm(OTf)₃ (1.97 g, 2.0 mmol) and KBpz (1.33 g, 4.0 mmol) were dissolved in THF (50 mL) and the solution was stirred for 48 h at room temperature. The THF was then removed under vacuum and the product extracted from the resulting

colourless solid with CH_2Cl_2 (50 mL). Removal of the CH_2Cl_2 *in vacuo* afforded the product as a colourless solid (1.59 g, 89 %).

EXAMPLE 9

$\text{Gd}(\text{Bpz})_2(\text{OTf})$

A mixture of $\text{Gd}(\text{OTf})_3$ (1.21 g, 2.0 mmol) and KBpz (1.33 g, 4.0 mmol) in THF (50 mL) was stirred for 20 h at room temperature. The solvent was removed under reduced pressure and the product extracted from the solid residue with CH_2Cl_2 (50 mL). Evaporation of the CH_2Cl_2 under reduced pressure gave the product as a pale yellow solid (1.29 g, 62 %).

EXAMPLE 10

$\text{Nd}(\text{Bpz})_2(\text{OTf})$

A mixture of $\text{Nd}(\text{OTf})_3$ (1.18 g, 2.0 mmol) and KBpz (1.33 g, 4.0 mmol) were dissolved in THF (50 mL) and the purple solution was stirred for 24 h at room temperature. A fine colourless precipitate developed within 1 h. After 24 h the solution was pink. The solvent was removed under vacuum and the product extracted from the resulting colourless solid with CH_2Cl_2 (50 mL). Removal of the CH_2Cl_2 *in vacuo* afforded the product as a purple solid (1.36 g, 77 %).

EXAMPLE 11**Ce(T_{Ind})₂(OTf)**

A mixture of Ce (OTf)₃ (0.59 g, 1.0 mmol) and KT_{Ind} (0.81 g, 2.0 mmol) in THF (50 mL) was stirred at room temperature under N₂ for 20 h. The THF was removed under reduced pressure to give a yellow residue. The product was extracted from the yellow residue with CH₂Cl₂ (50 mL). Removal of the CH₂Cl₂ *in vacuo* afforded the product as a pale yellow solid (0.55 g, 54 %).

EXAMPLE 12**Tb(T_{Ind})₂(OTf)**

A mixture of Tb(OTf)₃ (0.61g, 1.0 mmol) and KT_{Ind} (0.81 g, 2.0 mmol) in THF (50 mL) was allowed to stir for 16 h, by which time a colourless precipitate had formed. The THF was removed under reduced pressure and the pale yellow residue was treated with CH₂Cl₂ (50 mL) and the yellow supernatant filtered from the colourless precipitate. Removal of the CH₂Cl₂ under reduced pressure gave the product as a pale yellow solid (0.71 g, 69 %).

EXAMPLE 13**Eu(T_{Ind})₂(OTf)**

A mixture of Eu(OTf)₃ (0.60 g, 1.0 mmol) and KT_{Ind} (0.81 g, 2.0 mmol) in THF (50 mL) was stirred for 20 h at room temperature. The solvent was removed under reduced pressure and the product extracted from the solid residue with CH₂Cl₂ (50 mL). Evaporation

of the CH_2Cl_2 under reduced pressure gave the product as a pale yellow solid (0.59 g, 57 %).

EXAMPLE 14

$\text{Tm}(\text{T}_{\text{Ind}})_2(\text{OTf})$

$\text{Tm}(\text{OTf})_3$ (0.62 g, 1.0 mmol) and KT_{Ind} (0.81 g, 2.0 mmol) were dissolved in THF (50 mL) and the orange solution was stirred for 15 h at room temperature. The solvent was removed from the resulting cloudy solution and the yellow residue was washed with CH_2Cl_2 (50 mL). The yellow filtrate was evaporated to dryness under reduced pressure, affording the product as a pale yellow solid (0.68 g, 65 %).

EXAMPLE 15

$\text{Sm}(\text{T}_{\text{Ind}})_2(\text{OTf})$

$\text{Sm}(\text{OTf})_3$ (0.60 g, 1.0 mmol) and KT_{Ind} (0.81 g, 2.0 mmol) were dissolved in THF (50 mL) to give an orange cloudy solution. This mixture was stirred for 48 h and the solvent removed under reduced pressure. The product was isolated from the resulting yellow solid by extraction into CH_2Cl_2 and then removal of the solvent under reduced pressure (0.731 g, 72 %).

EXAMPLE 16

$\text{Gd}(\text{T}_{\text{Ind}})_2(\text{OTf})$

$\text{Gd}(\text{OTf})_3$ (1.21 g, 2.0 mmol) and KT_{Ind} (1.61 g, 4.0 mmol) were dissolved in THF (50 mL) to give a cloudy yellow solution. This

mixture was stirred for 16 h and then the solvent was removed. The product was extracted from the yellow residue with CH_2Cl_2 (50 mL) and isolated as a pale yellow powder upon removal of the CH_2Cl_2 *in vacuo* (1.59 g, 77 %).

EXAMPLE 17


$\text{Nd}(\text{T}_{\text{ind}})_2(\text{OTf})$

$\text{Nd}(\text{OTf})_3$ (1.18 g, 2.0 mmol) and KT_{ind} (1.61 g, 4.0 mmol) were dissolved in THF (50 mL) and the lilac solution was stirred for 24 h at room temperature. The solvent was removed from the resulting cloudy solution and the lilac residue was washed with CH_2Cl_2 (50 mL). The lilac filtrate was evaporated to dryness under reduced pressure, affording the product as a lilac solid (1.27 g, 62 %).


EXAMPLE 18

$\text{Tb}(\text{Bpz}^{12})_2(\text{OTf})$

$\text{Tb}(\text{OTf})_3$ (1.21 g, 2.0 mmol) and KBpz^{12} (2.23 g, 4.0 mmol) were suspended in THF (50 mL) and allowed to stir for 14 h. The initial colourless cloudy mixture cleared and became pale green during this time. The solvent was removed under reduced pressure and the colourless solid residue was extracted into CH_2Cl_2 (50 mL). The filtrate was concentrated to dryness to give the product as a colourless solid (2.00 g, 74 %).

EXAMPLE 19

$\text{Ce}(\text{OTf})_3$ (1.17 g, 2.0 mmol) and KBpz^{12} (2.23 g, 4.0 mmol) were suspended in THF (50 mL) and allowed to stir for 14 h. The initial colourless cloudy mixture cleared during this time. The solvent was removed under reduced pressure and the colourless solid residue was extracted into CH_2Cl_2 (50 mL). The filtrate was concentrated to dryness to give the product as a pale yellow/green solid (1.59 g, 83 %).

EXAMPLE 20

$\text{Tb}(\text{OTf})_3$ (1.20 g, 2.0 mmol) and KBpz^{12} (2.23 g, 4.0 mmol) were suspended in THF (50 mL) and allowed to stir for 14 h. The initial colourless cloudy mixture cleared and became yellow during this time. Analysis of the product at this time showed only 1 ligand coordinated to the metal centre. The mixture was then heated at 85 °C for 6 h after which time the mixture was cooled to room temperature and the solvent was removed under reduced pressure to give a yellow solid residue, which was extracted into CH_2Cl_2 (50 mL). The filtrate was concentrated to dryness to give the product as a pale yellow solid.

EXAMPLE 21**Tb(Bpz¹²)₂(OTf)**


Tb(OTf)₃ (1.20 g, 2.0 mmol) and KBpz¹² (2.23 g, 4.0 mmol) were suspended in THF (30 mL) and the mixture heated to reflux. After 6 h the mixture was cooled to room temperature and the solvent was removed under reduced pressure to give a yellow solid residue, which was extracted into CH₂Cl₂ (50 mL) and filtered from any insoluble residue. The filtrate was concentrated to dryness to give the product as a pale yellow solid.

EXAMPLE 22**Tb(Bpz¹⁴)₂(OTf)**

A mixture of Tb(OTf)₃ (0.61 g, 1.0 mmol) and KBpz¹² (1.11 g, 2.0 mmol) were suspended in THF (30 mL) and the mixture heated to reflux. After 7 h the mixture was cooled to room temperature and the solvent was removed under reduced pressure to give a yellow solid residue, which was extracted into CH₂Cl₂ (50 mL) and filtered from any insoluble residue. The filtrate was concentrated to dryness to give the product as a pale yellow solid (1.15 g, 86 %).

CLAIMS

1. Light emitting device comprising a complex containing a lanthanide metal cation complexed with from one to three polydentate ligands, wherein each ligand comprises one or more pyrazolyl groups, optionally substituted and optionally fused with a substituted or unsubstituted, heterocyclic or carbocyclic, aromatic or non-aromatic, ring system, one of the nitrogen atoms of the pyrazolyl groups forming a coordinate bond to the metal.
2. Device as claimed in claim 1, wherein the ligands are trispyrazolylborate anions, the pyrazolyl groups being optionally substituted and optionally fused with a substituted or unsubstituted, heterocyclic or carbocyclic, aromatic or non-aromatic, ring system, optionally substituted at the boron atom.
3. Device as claimed in claim 1 or claim 2, wherein the complex has the formula (I):



wherein Z is a carbon atom or R¹ - B fragment

p is 1, 2 or 3


q is 3-p and

A is a counterion

R¹ is: (i) hydrogen, aryl or aralkyl each optionally substituted with from one to five halogen or C₁ to C₆ alkyl groups; or (ii) C₁ to C₆ alkyl, C₁ to C₆ alkenyl or C₁ to C₆


alkynyl each optionally substituted with one or more halogen atoms

each L is covalently bound to Z and is independently selected from a group of the formula (II) or (III)



(II)

or



(III)


in which R², R³ and R⁴ are independently selected from: (i) halogen, cyano, nitro, sulphonyl, amino, C₁ to C₆ alkylamino, C₁ to C₆ alkylamido, carboxyl, C₁ to C₆ alkyloxycarbonyl, hydroxy, C₁ to C₆ alkoxy, C₁ to C₆ alkylcarbonyloxy, C₁ to C₆ alkylcarbonyl, C₁ to C₆ haloalkoxy and hydrogen; (ii) aryl or aralkyl each optionally substituted on the aryl ring or, for aralkyl, on the alkylene chain with from one or more of the groups mentioned under (i) above; and (iii) C₁ to C₆ alkyl, C₁ to C₆ alkenyl or C₁ to C₆ alkynyl each optionally substituted with one or more of the groups mentioned under (i) and (ii) above

or either R^2 and R^3 or R^3 and R^4 are linked so as to form a fused aromatic or non-aromatic, ring system with the pyrazolyl ring of L

and M is a trivalent lanthanide metal ion.

4. Device as claimed in any one of claims 1 to 3, wherein M is Tb, Ce, Eu, Er, Gd, Tm, Sm or Nd.
5. Device as claimed in any one of claims 1 to 4, wherein R^4 and/or R^2 is $-(CX_2)_nX$, wherein n is 0 or a positive integer from 1 to 6 and X is halogen, or orthohalogenated or orthodiperhalomethylated aryl.
6. Device as claimed in claim 5, wherein R^4 and/or R^2 is trifluoromethyl.
7. Device as claimed in any one of claims 1 to 6, wherein R^3 is hydrogen and R^4 and/or R^2 is trifluoromethyl.
8. Device as claimed in any one of claims 1 to 7, wherein Z is H-B.
9. Device as claimed in any one of claims 1 to 8, wherein the complex is positively charged and is derived from a compound containing $CF_3SO_3^-$, halide, nitrate or perchlorate as the counterion.
10. Device as claimed in any one of claims 1 to 9 which is a flat panel display.

11. Organometallic complex having the formula (I)



wherein Z, p, R¹, R², R³, R⁴, L, A, q and M are as defined in claim 1 and:

R⁴ and/or R² is -(CX₂)_nX wherein n is 0 or a positive integer from 1 to 6 and X is halogen; or R⁴ is orthodihalogenated or orthodiperhalomethylated aryl, optionally further substituted on the aryl ring; or

R² and R³ or R³ and R⁴ are linked so as to form a fused aromatic or non-aromatic ring system with the pyrazolyl ring of L.


12. Complex as claimed in claim 10, wherein M is Tb, Ce, Eu, Er, Gd, Tm, Sm or Nd.

13. Complex as claimed in claim 11 or claim 12, wherein R⁴ is trifluoromethyl.

14. Complex as claimed in any one of claims 11 to 13, wherein R³ is hydrogen and R² is trifluoromethyl.

15. Complex as claimed in any one of claims 11 to 14, wherein Z is H-B.

16. Complex as claimed in claim 11, wherein ZL_3 is



17. Complex as claimed in any one of claims 11 to 16, wherein A is $CF_3SO_3^-$, halide, nitrate or perchlorate.

18. Process for producing the complex of any one of claims 11 to 17 comprising the steps of reacting M^{3+} ions with ZL_3^- ions in solution and separating the complex from the reaction mixture.

19. Process as claimed in claim 18, wherein the complex is separated from the reaction mixture by solvent extraction.

20. Process as claimed in claim 18 or claim 19 which is carried out under substantially anhydrous conditions.

21. Light emitting material comprising an organometallic complex either as a film or dispersed within a matrix, the organometallic complex being a complex of a trivalent lanthanide metal with from 1 to 3 ligands wherein the ligands are optionally fluorinated and are arranged about the metal such that there are no carbon-hydrogen bonds within 5Å of the metal centre.

22. Light emitting material as claimed in claim 21, wherein the ligands are tridentate and there are two ligands per metal ion in the complex.

23. Light emitting material as claimed in claim 21 or claim 22, wherein the complex is a complex of any one of claims 11 to 17.

1/3




FIG. 1




FIG. 2

2/3.




FIG. 3




FIG. 4




FIG. 5




FIG. 6

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/GB 98/01587

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09K11/06 H05B33/14 C07D401/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09K H05B C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	ARMAROLI N ET AL: "Luminescence properties of Eu/sup 3+/, Tb/sup 3+/, and Gd/sup 3+ complexes of the hexadentate N-donor podand tris-3-(2-pyridyl)pyrazol-1ylhydroborate" CHEMICAL PHYSICS LETTERS, 26 SEPT. 1997, ELSEVIER, NETHERLANDS, vol. 276, no. 5-6, pages 435-440, XP002074915 ISSN 0009-2614 see page 435 - page 440	1-4, 11, 12
P, X	WO 98 06242 A (UNIV PRINCETON ; UNIV SOUTHERN CALIFORNIA (US)) 12 February 1998 see the whole document	1-3, 8, 10, 11
A	WO 93 11433 A (WALLAC OY) 10 June 1993 see the whole document	1-23

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"A" document member of the same patent family

Date of the actual completion of the international search

24 August 1998

Date of mailing of the international search report

03/09/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Drouot, M-C

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/01587

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9806242 A	12-02-1998	AU 3805297 A	25-02-1998
WO 9311433 A	10-06-1993	EP 0626068 A	30-11-1994
		US 5571897 A	05-11-1996